

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 964 431 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
23.01.2002 Bulletin 2002/04

(51) Int Cl.7: **C03C 3/091, H01J 61/34**

(21) Application number: **99110857.2**

(22) Date of filing: **07.06.1999**

(54) **Discharge lamp**

Entladungslampe

Lampe à décharge

(84) Designated Contracting States:
DE FR

(30) Priority: **12.06.1998 JP 16492298**
20.11.1998 JP 33064698

(43) Date of publication of application:
15.12.1999 Bulletin 1999/50

(73) Proprietor: **MATSUSHITA ELECTRIC INDUSTRIAL**
CO., LTD.
Kadoma-shi, Osaka (JP)

(72) Inventors:
• **Kiryu, Hideaki**
Takatsuki-shi, Osaka 569-1136 (JP)

• **Tanaka, Kazuhisa,**
c/o Matsushita Electronics Corp.
Ibaraki-shi, Osaka 567-0835 (JP)
• **Saitoh, Takeshi,**
Nishinomiya-shi, Hyogo 663-8112 (JP)

(74) Representative: **Flaccus, Rolf-Dieter, Dr.**
Patentanwalt Bussardweg 10
50389 Wesseling (DE)

(56) References cited:
EP-A- 0 601 391 **EP-A- 0 616 358**
US-A- 5 159 239 **US-A- 5 391 523**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 964 431 B1

Description

[0001] The present invention relates to a discharge lamp used for an automobile headlight, a light source for the backlight of a liquid crystal projector or the like.

5 [0002] A discharge lamp is provided with an arc tube having a pair of electrodes in a gas and uses light emitted by an arc discharge generated in the arc tube. In this discharge lamp, light emitted from the arc tube includes ultraviolet rays. Therefore, there was a problem in that the ultraviolet rays deteriorate the quality of various components such as a reflecting mirror, a front glass, etc., which are located in the vicinity of the discharge lamp. In order to eliminate such a problem, a discharge lamp in which an arc tube is enveloped by an outer tube containing additives capable of absorbing ultraviolet rays has been suggested. This discharge lamp is produced by inserting the arc tube into the outer tube and then fusing the end portion of the outer tube to the arc tube.

10 [0003] However, in the above-mentioned discharge lamp, both the outer tube and the arc tube are made of silica glass. Since the softening temperature of the outer tube is high and the same level as that of the arc tube, when the outer tube is fused to the arc tube, the arc tube also may be softened and deformed. The softening of the arc tube causes the electrodes located in the arc tube to deviate from the appropriate location, and, in turn, an arc generated between the electrodes to deviate, which may result in deteriorating the accuracy of luminous intensity distribution of the discharge lamp.

15 [0004] It is an object of the present invention to provide a discharge lamp achieving a high accuracy of luminous intensity distribution by inhibiting the deformation of the arc tube.

20 [0005] In order to achieve the above-mentioned object, a first discharge lamp of the present invention comprises an arc tube having a light-emitting portion provided with a pair of electrodes and an outer tube enveloping the light-emitting portion and at least partly fused to the arc tube. Herein, the outer tube contains silicon dioxide as a main component and further contains boron. With such a structure, the softening temperature of the outer tube can be made sufficiently lower than that of the arc tube. Thus, when the arc tube and outer tube are fused to each other, the deformation of the arc tube can be inhibited.

25 [0006] It is preferable in the first discharge lamp that the outer tube contains 0.12 weight % (referred to as wt.% hereinafter) or more of boron. Thus, the softening temperature of the outer tube can be adjusted to a more preferable temperature.

30 [0007] Furthermore, it is preferable in the first discharge lamp that the expression: $w_B/D \leq 120$ is satisfied, wherein w_B [wt.%] is the content of boron in the outer tube and D [mm] is the shortest distance between the inner surface of the outer tube and the external surface of the light-emitting portion. Thus, the softening temperature of the outer tube is inhibited from becoming excessively low. Furthermore, the outer tube is inhibited from deforming with the passage of the lighting time of the discharge lamp.

35 [0008] Still furthermore, it is preferable in the first discharge lamp that the expression: $w_B/L \leq 1.2$ is satisfied, wherein w_B [wt.%] is the content of boron in the outer tube and L [mm] is the shortest distance between the tip of the electrode located in the light-emitting portion and the portion where the outer tube and the arc tube are fused to each other. Thus, the softening temperature of the outer tube is inhibited from becoming excessively low. Furthermore, the fusing portion is inhibited from deforming with the passage of the lighting time of the discharge lamp.

40 [0009] Still furthermore, it is preferable in the first discharge lamp that the outer tube contains 90 to 99.88 wt.% of silicon dioxide.

45 [0010] In order to achieve the above-mentioned object, a second discharge lamp of the present invention comprises an arc tube having a light-emitting portion provided with a pair of electrodes, and an outer tube enveloping the light-emitting portion and being at least partly fused to the arc tube. Herein, the outer tube contains silicon dioxide as a main component and further contains at least one selected from aluminum and zirconium together with boron. With such a structure, since the softening temperature of the outer tube can be lowered and the processing temperature when the arc tube and the outer tube are fused can be lowered, the deformation of the arc tube can be inhibited.

[0011] It is preferable in the second discharge lamp that the expression: $(w_B + 2w_{Al} + 5w_{Zr}) \geq 0.12$ is satisfied, wherein w_B [wt.%] is the content of boron, w_{Al} [wt.%] is the content of aluminum and w_{Zr} [wt.%] is the content of zirconium in the outer tube.

50 [0012] Furthermore, it is preferable in the second discharge lamp that the expression: $(w_B + 2w_{Al} + 5w_{Zr})/D \leq 120$ is satisfied, wherein w_B [wt.%] is the content of boron, w_{Al} [wt.%] is the content of aluminum, w_{Zr} [wt.%] is the content of zirconium in the outer tube, and D [mm] is the shortest distance between the inner surface of the outer tube and the external surface of the light-emitting portion. Thus, the outer tube can be inhibited from deforming with the passage of the lighting time of the discharge lamp.

55 [0013] Still furthermore, it is preferable in the second discharge lamp that the expression: $(w_B + 2w_{Al} + 5w_{Zr})/L \leq 1.2$ is satisfied, wherein w_B [wt.%] is the content of boron, w_{Al} [wt.%] is the content of aluminum, w_{Zr} [wt.%] is the content of zirconium in the outer tube, and L [mm] is the shortest distance between the tip of the electrode located in the light-emitting portion and the portion where the outer tube and the arc tube are fused to each other. Thus, the fused

portion can be inhibited from deforming with the passage of the lighting time of the discharge lamp.

[0014] Still furthermore, it is preferable in the second discharge lamp that the outer tube contains 90 to 99.88 wt.% of silicon dioxide.

[0015] It is preferable in the first and second discharge lamps that the outer tube contains no more than 0.1 wt.% of at least one element selected from the group consisting of lithium, sodium, potassium, rubidium, cesium, beryllium, magnesium, calcium, strontium and barium.

[0016] Furthermore, it is preferable in the first and second discharge lamps that the outer tube further comprises at least one element selected from the group consisting of cerium, titanium, iron, praseodymium and europium. Thus, ultraviolet rays radiated from the discharge lamp can be reduced. Moreover, it is preferable that the content of the above-mentioned element in the outer tube is 0.01 to 1 wt.%.

[0017] Still further, it is preferable in the first and second discharge lamps that the expression: $P/D \leq 2000$ is satisfied, wherein P [W] is an electric power supplied to the discharge lamp and D [mm] is the shortest distance between the inner surface of the outer tube and the external surface of the light-emitting portion. Thus, the deformation of the outer tube due to the temperature increase in the outer tube during the lighting operation of the discharge lamp can be inhibited.

[0018] Fig. 1 is a cross-sectional view showing a structure of a discharge lamp of one example of the present invention.

[0019] Hereinafter, the present invention will be described by way of Examples with reference to the drawing.

[0020] Fig. 1 is a cross-sectional view showing a discharge lamp according to one example of the present invention.

[0021] An arc tube 1 comprises a spherical tubular light-emitting portion 1a forming a discharge space, flat sealing portions 1b and 1c that seal the both ends of the light-emitting portion 1a and a cylindrical side tube portion 1d provided continuously with the sealing portion 1c. The light-emitting portion 1a is provided with a pair of electrodes 5a and 5b and filled with mercury, metal halide and inert gas. One end of the electrode 5a is placed in the light-emitting portion 1a, and another end is connected to an outer lead wire 7a via a metal foil 6a embedded in the sealing portion 1c. Similarly, one end of the electrode 5b is placed in the light-emitting portion 1a and another end is connected to an outer lead wire 7b via a metal foil 6b embedded in the sealing portion 1b.

[0022] An outer tube 2 has an inner diameter that is larger than that of the light-emitting portion 1a. The arc tube 1 is inserted in the outer tube 2. The ends of the outer tube 2 are fused to the sealing portion 1b and the side tube portion 1d, respectively. In other words, the outer tube 2 is joined to the arc tube 1 so that it envelops the light-emitting portion 1a.

[0023] Furthermore, the arc tube 1 fused to the outer tube 2 is inserted into the concave portion formed in a base 3 and fixed with a support 4. Furthermore, the outer lead wire 7a is connected to a connection terminal 8a formed in the base 3, and the outer lead wire 7b is connected to a connection terminal 8b via a power supply line 9.

[0024] The arc tube 1 is made of silica glass. The softening temperature of the silica glass constituting the arc tube 1 is preferably 1600 to 1700 °C, more preferably 1650 to 1700 °C. The silica glass constituting the arc tube 1 preferably contains 90 wt.% or more of silicon dioxide, more preferably 95 wt.% or more, further preferably 98 wt.% or more. In addition, the silica glass may contain various kinds of elements as additives and impurities as long as the softening temperature of the glass is not excessively reduced and the glass is not devitrified with respect to visible light.

[0025] The outer tube 2 is made of silica glass. The silica glass constituting the outer tube 2 preferably contains silicon dioxide in the range from 90 to 99.88 wt.%, more preferably 95 to 99.8 wt.%, further preferably 97 to 99.5 wt.%.

[0026] The silica glass constituting the outer tube 2 has a softening temperature that is sufficiently lower than that of the silica glass constituting the arc tube 1. The softening temperature of the silica glass constituting the outer tube 2 is lower than that constituting the arc tube 1 preferably by 50 °C or more, more preferably by 100 °C or more. Specifically, the softening temperature is preferably 1650 °C or less, more preferably 1600 °C or less, and further preferably 1550 °C or less.

[0027] In order to achieve the above-mentioned softening temperature, the silica glass constituting the outer tube 2 contains additives capable of reducing the softening temperature. As such additives, at least one element selected from the group consisting of boron, aluminum and zirconium can be used. In particular, it is preferable that boron is used alone or in combination with at least one of aluminum and zirconium.

[0028] The greater the amount of the above-mentioned additives, the more the softening temperature of the silica glass can be lowered. Therefore, the lower limit of the content of the additives is specified as the amount capable of achieving the above-mentioned softening temperature. When boron is used alone as the additive, the content (w_B wt. %) is preferably 0.12 wt.% or more, more preferably 0.3 wt.% or more. On the other hand, when the boron is used in combination with at least one of aluminum and zirconium as the additives, the content of the additives preferably satisfies the expression: $(w_B + 2w_{Al} + 5w_{Zr}) \geq 0.12$, more preferably the expression: $(w_B + 2w_{Al} + 5w_{Zr}) \geq 0.3$. Herein, w_{Al} [wt. %] and w_{Zr} [wt. %] represent the contents of aluminum and zirconium, respectively.

[0029] Furthermore, it is preferable that the softening temperature of the silica glass constituting the outer tube 2 is sufficiently higher than the temperature the outer tube 2 reaches during the lighting operation of the discharge lamp. When the discharge lamp lights up, the light-emitting portion 1a is heated by the heat generated by the electrodes 5a

and 5b, subsequently the outer tube 2 is heated by the heat from the light-emitting portion 1a. Furthermore, the portion where the outer tube 2 and the arc tube 1 are fused to each other is heated by a heat conducted from the electrodes via a metal foil and the outer lead wire. Therefore, the temperature that the outer tube 2 reaches during the lighting operation of the discharge lamp depends upon the distance between the outer tube 2 and the light-emitting portion 1a, and the distance between the portion where the outer tube 2 and the arc tube 1 are fused to each other and the electrode.

[0030] Therefore, the softening temperature of the silica glass constituting the outer tube 2 can be determined by the distance between the outer tube 2 and the light-emitting portion 1a, more specifically by the shortest distance D [mm] between the inner surface of the outer tube 2 and the external surface of the light-emitting portion 1a. Moreover, D depends on an electric power P [W] that is supplied to the discharge lamp. Preferably, D is set so that the expression:

$P/D \leq 2000$ is satisfied. For example, in a 35 W lamp, D is usually 0.05 to 2 mm, preferably 0.1 to 2 mm.

[0031] Furthermore, the softening temperature can be determined by the distance between the portion where the outer tube 2 and the arc tube 1 are fused to each other and the electrode, more specifically the shortest distance L [mm] between the portion where the outer tube 2 and the arc tube 1 are fused to each other and the tip of the electrode located in the light-emitting portion 1a. Herein, L means the shortest distance among L_1 and L_2 . L_1 is a distance between the tip of the electrode 5a located in the light-emitting portion 1a and the portion where the inner surface of the outer tube 2 is in contact with the light-emitting portion 1a. L_2 is a distance between the tip of the electrode 5b located in the light-emitting portion 1a and the portion where the inner surface of the outer tube 2 is in contact with the light-emitting portion 1a. Moreover, L_1 and L_2 may be the same or different from each other. Furthermore, L is set based on the electric power supplied to the discharge lamp. For example, in a 35 W lamp, L is usually 3 to 5 mm, preferably 3.8 to 4.6 mm.

[0032] For example, in the case of a 35 W lamp, the softening temperature of the silica glass constituting the outer tube 2 is 1400 °C or more, and more preferably 1450 °C or more.

[0033] Therefore, the upper limit of the content of the above-mentioned additives can be specified by the distance between the outer tube 2 and the light-emitting portion 1a. When boron is used alone as the additive, the content of boron (w_B wt.%) preferably satisfies the expression: $w_B/D \leq 120$, more preferably $w_B/D \leq 100$. Moreover, when boron is used in combination with at least one of aluminum and zirconium as the additives, the contents of the elements preferably satisfy the expression: $(w_B + 2w_{Al} + 5w_{Zr})/D \leq 120$, more preferably the expression: $(w_B + 2w_{Al} + 5w_{Zr})/D \leq 100$.

[0034] Furthermore, the upper limit of the content of the above-mentioned additives also can be specified by the distance between the portion where the outer tube 2 and the arc tube 1 are fused to each other and the electrode. When boron is used alone as the additive, the content of boron (w_B wt. %) preferably satisfies the expression: $w_B/L \leq 1.2$, more preferably $w_B/L \leq 0.8$. Moreover, when boron is used in combination with at least one of aluminum and zirconium as the additives, the contents of the elements preferably satisfy the expression: $(w_B + 2w_{Al} + 5w_{Zr})/L \leq 1.2$, more preferably the expression: $(w_B + 2w_{Al} + 5w_{Zr})/L \leq 0.8$.

[0035] The content of boron in the silica glass constituting the outer tube 2 is preferably 0.04 to 2.0 wt.%, more preferably 0.1 to 1.8 wt.%, further preferably 0.5 to 1.5 wt.%. Moreover, the content of aluminum is preferably 0.02 to 1.0 wt.%, more preferably 0.05 to 0.8 wt.%, further preferably 0.05 to 0.5 wt.%. Moreover, the content of the zirconium is preferably 0.008 to 0.4 wt.%, more preferably 0.008 to 0.3 wt.%, further preferably in the range from 0.008 to 0.2 wt.%.

[0036] Moreover, the silica glass constituting the outer tube 2 preferably contains an element that absorbs ultraviolet rays. As such an element, at least one element selected from the group consisting of cerium, titanium, iron, praseodymium and europium can be used. The content of such an element is preferably 0.01 to 1 wt.%, more preferably 0.1 to 1.0 wt.%, and further preferably 0.2 to 0.8 wt.%.

[0037] Furthermore, the silica glass constituting the outer tube 2 may contain the other elements as additives and impurities. Examples of such elements include an alkaline metal such as lithium, sodium, potassium, rubidium, cesium, and the like, and an alkaline earth metal such as beryllium, magnesium, calcium, strontium, barium, and the like. However, the contents of the alkaline metal and alkaline earth metal are preferably 0.1 wt.% or less, more preferably 0.05 wt.% or less, and further preferably 0.03 wt.% or less, because too large a content of them may lead to the devitrification of the outer tube 2.

[0038] In the discharge lamp of the present invention, although the ultraviolet radiant quantity (k_{UV}) is not particularly limited, however, it is preferably 2.0×10^{-5} W/m or less, more preferably 1.0×10^{-5} W/m or less. Herein, the ultraviolet radiant quantity (k_{UV}) denotes a value expressed by the following equation:

$$K_{uv} = \frac{\int_{\lambda=250nm}^{400nm} E_e(\lambda) \cdot S(\lambda) \cdot d\lambda}{k_m \int_{\lambda=250nm}^{400nm} E_e(\lambda) \cdot v(\lambda) \cdot d\lambda}$$

$E_e(\lambda)$: spectral distribution of radiant flux [W]
 $v(\lambda)$: spectral luminous efficacy [l]
 λ : wavelength [nm]
 $S(\lambda)$: spectral load function [l]
 k_m : optical radiant equivalent (= 683 [lm/W])

[0039] Furthermore, the total luminous flux at the initial period of lighting operation of the lamp is preferably 2900 lm or more, more preferably 3000 lm or more. Furthermore, the luminous flux maintenance factor after 1000 hours of lighting operation is preferably 70 % or more, more preferably 75 % or more.

[0040] Furthermore, in the discharge lamp of the present invention, the general color rendering index (Ra) is preferably 60 or more, more preferably 65 or more.

[0041] In order to obtain such properties, it is preferable in the discharge lamp of the present invention that a mixture of sodium halide (NaX) and scandium halide (ScX₃) is used as the metal halide to be sealed in the light-emitting portion 1a. Furthermore, in this case, the weight ratio of NaX and ScX₃ is preferably in the range: 1 < NaX / ScX₃ < 20. Moreover, as the halide (X), I and Br preferably are used. Furthermore, as the inert gas, for example, xenon is preferably used.

Example 1

[0042] As shown in Table 1, sixteen types of outer tubes (Nos. 1 to 16) were produced by variously changing the contents of boron (w_B), aluminum (w_{Al}) and zirconium (w_{Zr}). Moreover, the outer tubes Nos. 1 to 16 contained 90 wt. % or more of silicon dioxide.

[0043] Discharge lamps having the same structure as FIG. 1 were produced by using the above-produced outer tubes. Silica glass containing 99.98 wt.% silicon dioxide and having a softening temperature of 1683 °C was used for an arc tube. 16 mg of NaI, 4 mg of ScI₃, 50mg of mercury and 7 atm of xenon gas were filled in the light-emitting portion. Moreover, the light-emitting portion had a content volume of 0.025cc and an arc length of 4.2mm.

[0044] The arc tube was inserted into the outer tube, and then the outer tube and the arc tube were fused to each other, thus forming a discharge lamp. The fusing temperature was as low as possible in the range capable of softening the outer tube to be used. The produced discharge lamps were visually observed for the deformation of the arc tube. The results are shown in Table 1. In Table 1, A indicates that the arc tube was not deformed; B indicates that the arc tube was slightly deformed; and C indicates that the arc tube is greatly deformed.

Table 1

Outer tube No.	Content of additives in the outer tube [wt.%]				Deformation of the arc tube
	w _B	w _{Al}	w _{Zr}	w _B + 2w _{Al} + 5w _{Zr}	
1	0.12	0	0	0.12	A
2	3.00	0	0	3.00	A
3	0.08	0.02	0	0.12	A
4	0.04	0.05	0	0.14	A
5	3.00	1.00	0	5.00	A
6	0.07	0	0.01	0.12	A
7	7.00	0	1.00	12.00	A
8	0.05	0.01	0.01	0.12	A
9	0.90	0.10	0.10	1.60	A
10	0.94	0.26	0.07	1.81	A

EP 0 964 431 B1

Table 1 (continued)

Outer tube No.	Content of additives in the outer tube [wt.%]				Deformation of the arc tube
	w_B	w_{Al}	w_{Zr}	$w_B + 2w_{Al} + 5w_{Zr}$	
11	2.96	0.45	0.32	5.46	A
12	5.00	1.00	1.00	12.00	A
13	0.01	0	0	0.10	B
14	0.05	0.02	0	0.09	B
15	0.05	0	0.01	0.10	B
16	0	0	0	0	C

[0045] As shown in Table 1, when the outer tubes Nos. 1 to 12 were used, the arc tubes were not deformed. When the outer tubes Nos. 13 to 15 were used, the arc tubes were slightly deformed. On the other hand, when the outer tube No. 16 without containing boron, aluminum or zirconium was used, the arc tube was greatly deformed.

Example 2

[0046] Discharge lamps were produced using the same arc tubes and outer tubes (Nos. 1 to 16) as Example 1 and by changing the distance between the inner face of the outer tube and the outer face of the arc tube (the distance shown by D in FIG. 1). The thus produced discharge lamps were observed visually for the deformation of the outer tube after 1000 hours of lighting operation with 35 W electric power. The results are shown in Table 2. In Table 2, A indicates that the outer tube was not deformed, and B indicates that the outer tube was deformed.

Table 2

Outer tube No.	Distance between the outer tube and the arc tube D[mm]			
	0.01	0.02	0.05	0.10
1	A	A	A	A
2	B	B	A	A
3	A	A	A	A
4	A	A	A	A
5	B	B	A	A
6	A	A	A	A
7	B	B	B	A
8	A	A	A	A
9	B	A	A	A
10	B	A	A	A
11	B	B	A	A
12	B	B	B	A
13	A	A	A	A
14	A	A	A	A
15	A	A	A	A
16	A	A	A	A

[0047] As shown in Table 2, when $(w_B + 2w_{Al} + 5w_{Zr})/D \leq 120$ was satisfied, the deformation of the outer tube was not observed. On the other hand, when $(w_B + 2w_{Al} + 5w_{Zr})/D > 120$ was satisfied, the deformation of the outer tube was observed.

Example 3

[0048] Discharge lamps were produced by using the same arc tubes and the outer tubes (Nos. 1 to 16) as Example 1 and by changing the shortest distance between the tip of the electrode and the fused portion of the arc tube and the outer tube (the distance shown by L in FIG. 1). The produced discharge lamps were observed visually for the deformation of the outer tube after 1000 hours of lighting operation with 35 W electric power. The results are shown in Table 3. In Table 3, A indicates that the fused portion was not deformed and B indicates that the fused portion was deformed.

Table 3

Outer tube No.	Distance between the fused portion of the outer tube and the arc tube and the electrode L[mm]			
	0.1	1.0	0.5	10.0
1	A	A	A	A
2	B	B	B	A
3	A	A	A	A
4	B	A	A	A
5	B	B	B	A
6	A	A	A	A
7	B	B	B	A
8	A	A	A	A
9	B	B	A	A
10	B	B	A	A
11	B	B	B	A
12	B	B	B	A
13	A	A	A	A
14	A	A	A	A
15	A	A	A	A
16	A	A	A	A

[0049] As shown in Table 3, when the expression: $(w_B + 2w_{Al} + 5w_{Zr})/L \leq 1.2$ is satisfied, the deformation was not observed in the fused portion of the outer tube and the arc tube. On the other hand, when the expression: $(w_B + 2w_{Al} + 5w_{Zr})/L > 1.2$ is satisfied, the deformation was observed in the fused portion.

Example 4

[0050] Seven types of outer tubes (Nos. 17 to 23) were produced by using silica glass containing boron, aluminum and zirconium and by variously changing the contents of potassium (w_K) and barium (w_{Ba}), as shown in Table 4. Moreover, the outer tubes (No. 17 to 23) contained 90 wt.% or more of silicon dioxide.

[0051] By using the thus produced outer tubes, discharge lamps having the same structure as FIG. 1 were produced. As the arc tube, the same arc tube as Example 1 was used. The arc tube was inserted into the outer tube, and then the outer tube and the arc tube were fused to each other, thus forming a discharge lamp. The fusing temperature was made to be as low as possible in the range capable of softening the outer tube to be used. The produced discharge lamps were observed visually for devitrification of the outer tubes after 1000 hours of lighting operation with 35 W electric power. The results are shown in Table 4. In Table 4, A indicates that the devitrification of the outer tube was not observed and B indicates that the devitrification of the outer tube was observed.

Table 4

Outer tube No.	Content of additives in the outer tube [wt.%]					Devitrification of the outer tube
	w _B	w _{Al}	w _{Zr}	w _K	w _{Ba}	
17	1.00	0.30	0.07	0	0	A
18	1.00	0.30	0.07	0.10	0	A
19	1.00	0.30	0.07	0	0.10	A
20	1.00	0.30	0.07	0.02	0.08	A
21	1.00	0.30	0.07	0.12	0	B
22	1.00	0.30	0.07	0	0.15	B
23	1.00	0.30	0.07	0.08	0.04	B

[0052] As shown in Table 4, when the outer tubes Nos. 17 to 20 were used, the devitrification of the outer tubes were not observed. On the other hand, when the outer tubes No. 21 to 23 were used, the devitrification of the outer tube was observed.

Example 5

[0053] Fourteen types of outer tubes (Nos. 24 to 37) were produced by using silica glass containing boron, aluminum and zirconium and by variously changing the contents of cerium (w_{Ce}), titanium (w_{Ti}), iron (w_{Fe}), praseodymium (w_{Pr}) and europium (w_{Eu}), as shown in Table 5. Moreover, the outer tubes No. 24 to 37 contained 90 wt.% or more of silicon dioxide.

[0054] By using the thus produced outer tubes, discharge lamps having the same structure as FIG. 1 were produced. As the arc tube, the same arc tube as Example 1 was used. The arc tube was inserted into the outer tube, and then the outer tube and arc tube were fused to each other, thus forming a discharge lamp. When the produced discharge lamps were lighted up with 35 W electric power, ultraviolet rays radiant quantities (K_{UV}) and the total luminous flux at the initial period of lighting operation were examined. The results are shown in Table 5.

Table 5

Outer tube No	Content of additives in the outer tube [wt. %]								K _{UV} [10 ⁻⁵ W/ lm]	Total luminous flux [lm]
	W _B	W _{Al}	W _{Zr}	W _{Ce}	W _{Ti}	W _{Fe}	W _{Pr}	W _{Eu}		
24	0.90	0.20	0.01	0.01	0	0	0	0	1.98	3250
25	0.90	0.20	0.01	0	0.01	0	0	0	1.85	3240
26	0.90	0.20	0.01	0	0	0.01	0	0	1.95	3270
27	0.90	0.20	0.01	0	0	0	0.01	0	1.76	3240
28	0.90	0.20	0.01	0	0	0	0	0.01	1.88	3260
29	0.90	0.20	0.01	1.00	0	0	0	0	0.07	3100
30	0.90	0.20	0.01	0	1.00	0	0	0	0.11	3080
31	0.90	0.20	0.01	0	0	1.00	0	0	0.03	3010
32	0.90	0.20	0.01	0	0	0	1.00	0	0.11	3040
33	0.90	0.20	0.01	0	0	0	0	1.00	0.23	3030
34	0.90	0.20	0.01	3.00	0	0	0	0	0.03	2840
35	0.90	0.20	0.01	0	3.00	0	0	0	0.04	2860
36	0.90	0.20	0.01	0	0	3.00	0	0	0.02	2760
37	0.90	0.20	0.01	0	0	0	0	0	2.25	3260

[0055] As shown in Table 5, when the outer tubes Nos. 24 to 36 containing cerium, titanium, iron, praseodymium or europium were used, k_{UV} was lower by about 10 % or more than the case where the outer tube No. 37 without containing the above-mentioned elements was used. Furthermore, when the outer tubes Nos. 24 to 33 containing less than 1 wt. % of cerium, titanium, iron, praseodymium and europium were used, high total luminous flux could be obtained.

Claims

1. A discharge lamp comprising

an arc tube having a light-emitting portion provided with a pair of electrodes and
an outer tube enveloping said light-emitting portion and being at least partly fused to said arc tube,

wherein said outer tube contains silicon dioxide as a main component and further contains boron.

2. The discharge lamp according to claim 1, wherein said outer tube contains 0.12 wt.% or more of boron.

3. The discharge lamp according to claim 1, satisfying

$$w_B \text{ [wt.\%]} / D \text{ [mm]} \leq 120$$

wherein w_B is the content of boron in said outer tube and D is the shortest distance between an inner surface of said outer tube and an external surface of said light-emitting portion.

4. The discharge lamp according to claim 1, satisfying

$$w_B \text{ [wt.\%]} / L \text{ [mm]} \leq 1.2$$

wherein w_B is the content of boron in said outer tube and L is the shortest distance between a tip of one of said electrodes located in said light-emitting portion and the portion where said outer tube and said arc tube are fused to each other.

5. The discharge lamp according to claim 1, wherein said outer tube contains 90 to 99.88 wt.% of silicon dioxide.

6. The discharge lamp according to claim 1, wherein said outer tube contains no more than 0.1 wt.% of at least one element selected from the group consisting of lithium, sodium, potassium, rubidium, cesium, beryllium, magnesium, calcium, strontium and barium.

7. The discharge lamp according to claim 1, wherein said outer tube further comprises at least one element selected from the group consisting of cerium, titanium, iron, praseodymium and europium.

8. The discharge lamp according to claim 7, wherein the content of at least one element selected from the group consisting of cerium, titanium, iron, praseodymium and europium in said outer tube is 0.01 to 1 wt. %.

9. The discharge lamp according to claim 1, satisfying

$$P[W]/D \text{ [mm]} \leq 2000$$

wherein P is an electric power supplied to said discharge lamp and D is the shortest distance between an inner surface of said outer tube and an external surface of said light-emitting portion.

10. A discharge lamp comprising

an arc tube having a light-emitting portion provided with a pair of electrodes and
an outer tube enveloping said light-emitting portion and being at least partly fused to said arc tube,

wherein said outer tube contains silicon dioxide as a main component and further contains at least one selected from aluminum and zirconium together with boron.

11. The discharge lamp according to claim 10, satisfying

$$(w_B [\text{wt.}\%] + 2w_{Al} [\text{wt.}\%] + 5w_{Zr} [\text{wt.}\%]) \geq 0.12$$

wherein w_B is the content of boron, w_{Al} is the content of aluminum and w_{Zr} is the content of zirconium in said outer tube.

12. The discharge lamp according to claim 10, satisfying

$$(w_B [\text{wt.}\%] + 2w_{Al} [\text{wt.}\%] + 5w_{Zr} [\text{wt.}\%]) / D [\text{mm}] \leq 120$$

wherein w_B is the content of boron, w_{Al} is the content of aluminum, w_{Zr} is the content of zirconium in said outer tube, and D is the shortest distance between an inner surface of said outer tube and an external surface of said light-emitting portion.

13. The discharge lamp according to claim 10, satisfying

$$(w_B [\text{wt.}\%] + 2w_{Al} [\text{wt.}\%] + 5w_{Zr} [\text{wt.}\%]) / L [\text{mm}] \leq 1.2$$

wherein w_B is the content of boron, w_{Al} is the content of aluminum, w_{Zr} is the content of zirconium in said outer tube, and L is the shortest distance between a tip of one of said electrodes located in said light-emitting portion and a portion where said outer tube and said arc tube are fused to each other.

14. The discharge lamp according to claim 10, wherein said outer tube contains 90 to 99.88 wt. % of silicon dioxide.

15. The discharge lamp according to claim 10, wherein said outer tube contains no more than 0.1 wt.% of at least one element selected from the group consisting of lithium, sodium, potassium, rubidium, cesium, beryllium, magnesium, calcium, strontium and barium.

16. The discharge lamp according to claim 10, wherein said outer tube further comprises at least one element selected from the group consisting of cerium, titanium, iron, praseodymium and europium.

17. The discharge lamp according to claim 16, wherein the content of at least one element selected from the group consisting of cerium, titanium, iron, praseodymium and europium in said outer tube is 0.01 to 1 wt. %.

18. The discharge lamp according to claim 10, satisfying

$$P [\text{W}] / D [\text{mm}] \leq 2000$$

wherein P is an electric power supplied to said discharge lamp and D is the shortest distance between an inner surface of said outer tube and an external surface of said light-emitting portion.

Patentansprüche

1. Entladungslampe, umfassend

eine Lichtbogen-Röhre, die einen lichtemittierenden Bereich aufweist, der mit einem Paar Elektroden versehen ist, und
eine äußere Röhre, die den lichtemittierenden Bereich umgibt und zumindest teilweise mit der Lichtbogen-Röhre verschmolzen ist,

EP 0 964 431 B1

wobei die äußere Röhre Siliziumdioxid als Hauptbestandteil enthält und überdies Bor enthält.

2. Entladungslampe nach Anspruch 1, wobei die äußere Röhre $\geq 0,12$ Gew.-% Bor enthält.

5 3. Entladungslampe nach Anspruch 1, die

$$w_B [\text{Gew.-%}] / D [\text{mm}] \leq 120$$

10 erfüllt,
wobei w_B der Gehalt an Bor in der äußeren Röhre ist und D der kürzeste Abstand zwischen der inneren Oberfläche der äußeren Röhre und der äußeren Oberfläche des lichtemittierenden Bereichs.

15 4. Entladungslampe nach Anspruch 1, die

$$w_B [\text{Gew.-%}] / L [\text{mm}] \leq 1,2$$

20 erfüllt,
wobei w_B der Gehalt an Bor in der äußeren Röhre ist und L der kürzeste Abstand zwischen der Spitze einer der Elektroden in dem lichtemittierenden Bereich und dem Bereich, in dem die äußere Röhre und die Lichtbogen-Röhre miteinander verschmolzen sind.

25 5. Entladungslampe nach Anspruch 1, wobei die äußere Röhre 90 bis 99,88 Gew.-% Siliziumdioxid enthält.

6. Entladungslampe nach Anspruch 1, wobei die äußere Röhre nicht mehr als 0,1 Gew.-% von zumindest einem Element enthält, das aus der Gruppe ausgewählt ist, die aus Lithium, Natrium, Kalium, Rubidium, Cäsium, Beryllium, Magnesium, Calcium, Strontium und Barium besteht.

30 7. Entladungslampe nach Anspruch 1, wobei die äußere Röhre zusätzlich zumindest ein Element umfaßt, das aus der Gruppe ausgewählt ist, die aus Cer, Titan, Eisen, Praseodym und Europium besteht.

8. Entladungslampe nach Anspruch 7, wobei der Gehalt zumindest eines Elements, das aus der Gruppe ausgewählt ist, die aus Cer, Titan, Eisen, Praseodym und Europium besteht, 0,01 bis 1 Gew.-% beträgt.

35 9. Entladungslampe nach Anspruch 1, die

$$P [\text{W}] / D [\text{mm}] \leq 2000$$

40 erfüllt,
wobei P die elektrische Leistung ist, die an die Entladungslampe geliefert wird, und D der kürzeste Abstand zwischen der inneren Oberfläche der äußeren Röhre und der äußeren Oberfläche des lichtemittierenden Bereichs.

45 10. Entladungslampe, umfassend

eine Lichtbogen-Röhre, die einen lichtemittierenden Bereich aufweist, der mit einem Paar Elektroden versehen ist, und

50 eine äußere Röhre, die den lichtemittierenden Bereich umgibt und zumindest teilweise mit der Lichtbogen-Röhre verschmolzen ist,

wobei die äußere Röhre Siliziumdioxid als Hauptbestandteil enthält und überdies zumindest eines der beiden Metalle Aluminium und Zirkon zusammen mit Bor enthält.

55 11. Entladungslampe nach Anspruch 10, die

$$(w_B [\text{Gew.-%}] + 2w_{Al} [\text{Gew.-%}] + 5w_{Zr} [\text{Gew.-%}]) \geq 0,12$$

EP 0 964 431 B1

erfüllt,
wobei w_B der Gehalt an Bor ist, w_{Al} der Gehalt an Aluminium und w_{Zr} der Gehalt an Zirkon in der äußeren Röhre.

12. Entladungslampe nach Anspruch 10, die

$$(w_B [\text{Gew.}\%] + 2w_{Al} [\text{Gew.}\%] + 5w_{Zr} [\text{Gew.}\%]) / D [\text{mm}] \leq 120$$

erfüllt,
wobei w_B der Gehalt an Bor ist, w_{Al} der Gehalt an Aluminium und w_{Zr} der Gehalt an Zirkon in der äußeren Röhre, und D der kürzeste Abstand zwischen der inneren Oberfläche der äußeren Röhre und der äußeren Oberfläche des lichtemittierenden Bereichs ist.

13. Entladungslampe nach Anspruch 10, die

$$(w_B [\text{Gew.}\%] + 2w_{Al} [\text{Gew.}\%] + 5w_{Zr} [\text{Gew.}\%]) / L [\text{mm}] \leq 1,2$$

erfüllt,
wobei w_B der Gehalt an Bor ist, w_{Al} der Gehalt an Aluminium, w_{Zr} der Gehalt an Zirkon in der äußeren Röhre, und L der kürzeste Abstand zwischen der Spitze einer der Elektroden ist, die in dem lichtemittierenden Bereich lokalisiert ist, und dem Bereich, in dem die äußere Röhre und die Lichtbogen-Röhre miteinander verschmolzen sind.

14. Entladungslampe nach Anspruch 10, wobei die äußere Röhre 90 bis 99,88 Gew.-% Siliziumdioxid enthält.

15. Entladungslampe nach Anspruch 10, wobei die äußere Röhre nicht mehr als 0,1 Gew.-% von zumindest einem Element enthält, das aus der Gruppe ausgewählt ist, die aus Lithium, Natrium, Kalium, Rubidium, Cäsium, Beryllium, Magnesium, Calcium, Strontium und Barium besteht.

16. Entladungslampe nach Anspruch 10, wobei die äußere Röhre zusätzlich zumindest ein Element umfaßt, daß aus der Gruppe ausgewählt ist, die aus Cer, Titan, Eisen, Praseodym und Europium besteht.

17. Entladungslampe nach Anspruch 16, wobei der Gehalt zumindest eines Elements, das aus der Gruppe ausgewählt ist, die aus Cer, Titan, Eisen, Praseodym und Europium besteht, 0,01 bis 1 Gew.-% beträgt.

18. Entladungslampe nach Anspruch 10, die

$$P [\text{W}] / D [\text{mm}] \leq 2000$$

erfüllt,
wobei P die elektrische Leistung ist, die an die Entladungslampe geliefert wird, und D der kürzeste Abstand zwischen der inneren Oberfläche der äußeren Röhre und der äußeren Oberfläche des lichtemittierenden Bereichs.

Revendications

1. Lampe à décharge comprenant :

un tube à arc comportant une partie électro-luminescente pourvue d'une paire d'électrodes et
un tube externe enveloppant ladite partie électro-luminescente et étant au moins partiellement réunie par fusion audit tube à arc, dans laquelle ledit tube externe contient du dioxyde de silicium comme composant principal et contient en outre du bore.

2. Lampe à décharge selon la revendication 1, dans laquelle ledit tube externe contient 0,12 % en poids ou plus de bore.

EP 0 964 431 B1

3. Lampe à décharge selon la revendication 1, satisfaisant :

$$w_B [\% \text{ en poids}]/D [\text{mm}] \leq 120$$

dans laquelle w_B est la teneur en bore dudit tube externe et D la distance la plus courte entre une surface interne dudit tube externe et une surface externe de ladite partie électro-luminescente.

4. Lampe à décharge selon la revendication 1, satisfaisant :

$$w_B [\% \text{ en poids}]/L [\text{mm}] \leq 1,2$$

dans laquelle w_B est la teneur en bore dudit tube externe et L est la distance la plus courte entre une pointe d'une desdites électrodes située dans ladite partie électro-luminescente et la partie dans laquelle ledit tube externe et ledit tube à arc sont réunis entre eux par fusion.

5. Lampe à décharge selon la revendication 1, dans laquelle ledit tube externe contient 90 à 99,88 % en poids de dioxyde de silicium.

6. Lampe à décharge selon la revendication 1, dans laquelle ledit tube externe ne contient pas plus de 0,1 % en poids d'au moins un élément choisi dans le groupe constitué de lithium, sodium, potassium, rubidium, césium, béryllium, magnésium, calcium, strontium et baryum.

7. Lampe à décharge selon la revendication 1, dans laquelle ledit tube externe comporte en outre au moins un élément choisi dans le groupe constitué de cérium, titane, fer, praséodymium et europium.

8. Lampe à décharge selon la revendication 7, dans laquelle la teneur d'au moins un élément choisi dans le groupe constitué de cérium, titane, fer, praséodymium et europium dans ledit tube externe est de 0,01 à 1 % en poids.

9. Lampe à décharge selon la revendication 1, satisfaisant :

$$P [\text{W}]/D [\text{mm}] \leq 2000$$

dans laquelle P est une alimentation électrique appliquée à ladite lampe à décharge et D la distance la plus courte entre une surface interne dudit tube externe et une surface externe de ladite partie électro-luminescente.

10. Lampe à décharge comprenant :

un tube à arc comportant une partie électro-luminescente pourvue d'une paire d'électrodes et un tube externe enveloppant ladite partie électro-luminescente et étant au moins partiellement réunie par fusion audit tube à arc,

dans lequel ledit tube externe contient du dioxyde de silicium comme composant principal et contient en outre au moins un élément choisi parmi l'aluminium et le zirconium associé à du bore.

11. Lampe à décharge selon la revendication 10, satisfaisant :

$$(w_B [\% \text{ en poids}] + 2w_{Al} [\% \text{ en poids}] + 5w_{Zr} [\% \text{ en poids}]) \geq 0,12$$

dans laquelle w_B est la teneur en bore, $2w_{Al}$ est la teneur en aluminium et $5w_{Zr}$ est la teneur en zirconium dudit tube externe.

12. Lampe à décharge selon la revendication 10, satisfaisant :

EP 0 964 431 B1

$$(w_B [\% \text{ en poids}] + 2w_{Al} [\% \text{ en poids}] + 5w_{Zr} [\% \text{ en poids}])/D [\text{mm}] \leq 120$$

dans laquelle w_B est la teneur en bore, $2w_{Al}$ est la teneur en aluminium et $5w_{Zr}$ est la teneur en zirconium dudit tube externe, et D est la distance la plus courte entre une surface interne dudit tube externe et une surface externe de ladite partie électro-luminescente.

13. Lampe à décharge selon la revendication 10, satisfaisant :

$$(w_B [\% \text{ en poids}] + 2w_{Al} [\% \text{ en poids}] + 5w_{Zr} [\% \text{ en poids}])/L [\text{mm}] \leq 1,2$$

dans laquelle w_B est la teneur en bore, $2w_{Al}$ est la teneur en aluminium et $5w_{Zr}$ est la teneur en zirconium dudit tube externe, et L est la distance la plus courte entre une pointe de l'une desdites électrodes située dans ladite partie électro-luminescente et une partie dans laquelle ledit tube externe est ledit tube à arc sont réunis entre eux par fusion.

14. Lampe à décharge selon la revendication 10, dans laquelle ledit tube externe contient 90 à 99,88 % en poids de dioxyde de silicium.

15. Lampe à décharge selon la revendication 10, dans laquelle ledit tube externe ne contient pas plus de 0,1 % en poids d'au moins un élément choisi dans le groupe constitué de lithium, sodium, potassium, rubidium, césium, béryllium, magnésium, calcium, strontium et baryum.

16. Lampe à décharge selon la revendication 10, dans laquelle ledit tube externe comprend en outre au moins un élément choisi dans le groupe constitué de cérium, titane, fer, praséodymium et europium.

17. Lampe à décharge selon la revendication 16, dans laquelle la teneur en au moins un élément choisi dans le groupe constitué de cérium, titane, fer, praséodymium et europium dudit tube externe est de 0,01 à 1 % en poids.

18. Lampe à décharge selon la revendication 10, satisfaisant :

$$P [W]/D [\text{mm}] \leq 2000$$

dans laquelle P est une alimentation électrique appliquée à ladite lampe à décharge et D est la distance la plus courte entre une surface interne dudit tube externe et une surface externe de ladite partie électro-luminescente.




FIG. 1